




CrazyDrill Cool XL 15 x d

ANWENDUNGSEMPFEHLUNG

● Sehr gut geeignet | ● Gut geeignet | ○ bedingt geeignet | ☒ Nicht empfohlen



BOHREN MIT INNENKÜHLUNG | SCHNITTDATENÜBERSICHT



| Werkstoffgruppe | Werkstoff | Wr.Nr. | DIN | AISI/ASTM/UNS | v _c [m/min] | Q ₁ | Q _x | f [mm/U] | | | | | | | | | | | | | | | | | | | | | |
|--|---|------------------------------------|-------------------------|-----------------------|---------------------------|----------------|----------------|-------------|--------------|-------------------|-------------|--------------------------|------------------|-------------------|---------------------------|-------------|-----------------------|-------|-------|---|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| | | | | | | | | 1.0 mm f | 1.25 mm f | 1.5 mm 1/16" f | 2.0 mm f | Ød1 2.5 mm 3/32" f | 3.0 mm 1/8" f | 4.0 mm 5/32" f | 5.0 mm 3/16" - 7/32" f | 6.0 mm f | | | | | | | | | | | | | |
| P | Stähle unlegiert Rm < 800 N/mm ² | 1.0301 | C10 | AISI 1010 | 60-140 | 15xd1 | - | 0.040 | 0.050 | 0.060 | 0.080 | 0.090 | 0.120 | 0.160 | 0.180 | 0.200 | | | | | | | | | | | | | |
| | | 1.0401 | C15 | AISI 1015 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 1.1191 | C45E/CK45 | AISI 1045 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 1.0044 | S275JR | AISI 1020 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 1.0715 | 11SMn30 | AISI 1215 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 1.5752 | 15NiCr13 | ASTM 3415 / AISI 3310 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | Stähle niedriglegiert Rm > 900 N/mm ² | 1.7131 | 16MnCr5 | AISI 5115 | 50-130 | 15xd1 | - | 0.040 | 0.050 | 0.060 | 0.080 | 0.090 | 0.120 | 0.160 | 0.180 | 0.200 | | | | | | | | | | | | | |
| | | 1.3505 | 100Cr6 | AISI 52100 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 1.7225 | 42CrMo4 | AISI 4140 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 1.2842 | 90MnCrV8 | AISI O2 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 1.2379 | X153CrMoV12 | AISI D2 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 1.2436 | X210CrW12 | AISI D4/D6 | | | | | | | | | | | | | | | | | | | | | | | | | |
| Werkzeugstähle hochlegiert Rm < 1200 N/mm ² | 1.3343 | HS6-5-2C | AISI M2 / UNS T11302 | 40-100 | 15xd1 | - | 0.030 | 0.040 | 0.050 | 0.070 | 0.080 | 0.090 | 0.120 | 0.150 | 0.180 | | | | | | | | | | | | | | |
| | 1.3355 | HS18-0-1 | AISI T1 / UNS T12001 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | M | Rostfreie Stähle- ferritisch | 1.4016 | | | | | | | | | | | | | X6Cr17 | AISI 430 / UNS S43000 | 30-60 | 15xd1 | - | 0.020 | 0.040 | 0.060 | 0.080 | 0.100 | 0.130 | 0.150 | 0.200 | 0.220 |
| | | | 1.4105 | | | | | | | | | | | | | X6CrMoS17 | AISI 430F | | | | | | | | | | | | |
| | | Rostfreie Stähle- martensitisch | 1.4034 | | | | | | | | | | | | | X46Cr13 | AISI 420C | 40-80 | 15xd1 | - | 0.040 | 0.060 | 0.080 | 0.100 | 0.120 | 0.150 | 0.180 | 0.200 | 0.220 |
| | | | 1.4112 | | | | | | | | | | | | | X90CrMoV18 | AISI 440B | | | | | | | | | | | | |
| Rostfreie Stähle- martensitisch - PH | 1.4542 | X5CrNiCuNb 16-4 | AISI 630 / ASTM 17-4 PH | 30-60 | 5xd1 | 2xd1 | 0.020 | 0.030 | 0.040 | 0.060 | 0.070 | 0.100 | 0.120 | 0.150 | 0.180 | | | | | | | | | | | | | | |
| | 1.4545 | X5CrNiCuNb 15-5 | ASTM 15-5 PH | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Rostfreie Stähle- austenitisch | 1.4301 | X5CrNi 18-10 | AISI 304 | 30-60 | 5xd1 | 2xd1 | 0.020 | 0.030 | 0.040 | 0.060 | 0.070 | 0.100 | 0.120 | 0.150 | 0.180 | | | | | | | | | | | | | | |
| | 1.4435 | X2CrNiMo 18-14-3 | AISI 316L | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | 1.4441 | X2CrNiMo 18-15-3 | AISI 316LM | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | 1.4539 | X1NiCrMoCu 25-20-5 | AISI 904L | | | | | | | | | | | | | | | | | | | | | | | | | | |
| K | Gusseisen | 0.6020 | GG20 | ASTM 30 | 80-150 | 15xd1 | - | 0.050 | 0.060 | 0.070 | 0.080 | 0.090 | 0.160 | 0.200 | 0.250 | 0.300 | | | | | | | | | | | | | |
| | | 0.6030 | GG30 | ASTM 40B | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 0.7040 | GGG40 | ASTM 60-40-18 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 0.7060 | GGG60 | ASTM 80-60-03 | | | | | | | | | | | | | | | | | | | | | | | | | |
| N | Aluminium Knetlegierungen | 3.2315 | AlMgSi1 | ASTM 6351 | 100-200 | 15xd1 | - | 0.050 | 0.060 | 0.080 | 0.120 | 0.160 | 0.180 | 0.200 | 0.250 | 0.300 | | | | | | | | | | | | | |
| | | 3.4365 | AlZnMgCu1.5 | ASTM 7075 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | Aluminium Druckgusslegierungen | 3.2163 | GD-AlSi9Cu3 | ASTM A380 | 80-150 | 15xd1 | - | 0.050 | 0.060 | 0.080 | 0.100 | 0.120 | 0.150 | 0.200 | 0.250 | 0.300 | | | | | | | | | | | | | |
| | | 3.2381 | GD-AlSi10Mg | UNS A03590 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | Kupfer | 2.0040 | Cu-OF / CW008A | UNS C10100 | 40-80 | 2xd1 | 2xd1 | 0.025 | 0.045 | 0.065 | 0.085 | 0.110 | 0.140 | 0.160 | 0.180 | 0.200 | | | | | | | | | | | | | |
| | | 2.0065 | Cu-ETP / CW004A | UNS C11000 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | Messing bleifrei | 2.0321 | CuZn37 CW508L | UNS C27400 | 40-80 | 2xd1 | 2xd1 | 0.025 | 0.045 | 0.065 | 0.085 | 0.110 | 0.140 | 0.160 | 0.180 | 0.200 | | | | | | | | | | | | | |
| | | 2.0360 | CuZn40 CW509L | UNS C28000 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | Messing, Bronze Rm < 400 N/mm ² | 2.0401 | CuZn39Pb3 / CW614N | UNS C38500 | 50-120 | 15xd1 | - | 0.040 | 0.050 | 0.060 | 0.090 | 0.120 | 0.130 | 0.170 | 0.220 | 0.240 | | | | | | | | | | | | | |
| | | 2.1020 | CuSn6 | UNS C51900 | | | | | | | | | | | | | | | | | | | | | | | | | |
| Bronze Rm < 600 N/mm ² | 2.0966 | CuAl10Ni5Fe4 | UNS C63000 | 40-80 | 15xd1 | - | 0.025 | 0.045 | 0.065 | 0.085 | 0.110 | 0.120 | 0.160 | 0.200 | 0.220 | | | | | | | | | | | | | | |
| | 2.0960 | CuAl9Mn2 | UNS C63200 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| S ₁ | Hitzebeständige Stähle | 2.4856 | | Inconel 625 | 25-50 | 3xd1 | 1xd1 | 0.010 | 0.020 | 0.030 | 0.040 | 0.050 | 0.065 | 0.080 | 0.100 | 0.120 | | | | | | | | | | | | | |
| | | 2.4668 | | Inconel 718 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 2.4617 | NiMo28 | Hastelloy B-2 | | | | | | | | | | | | | | | | | | | | | | | | | |
| | | 2.4665 | NiCr22Fe18Mo | Hastelloy X | | | | | | | | | | | | | | | | | | | | | | | | | |
| S ₂ | Titan rein | 3.7035 | Gr.2 | ASTM B348 / F67 | 25-50 | 3xd1 | 1xd1 | 0.010 | 0.020 | 0.030 | 0.040 | 0.050 | 0.065 | 0.080 | 0.100 | 0.120 | | | | | | | | | | | | | |
| | | 3.7065 | Gr.4 | ASTM B348 / F68 | | | | | | | | | | | | | | | | | | | | | | | | | |
| S ₂ | Titan Legierungen | 3.7165 | TiAl6V4 | ASTM B348 / F136 | 20-40 | 5xd1 | 1xd1 | 0.010 | 0.020 | 0.030 | 0.040 | 0.050 | 0.065 | 0.080 | 0.100 | 0.120 | | | | | | | | | | | | | |
| | | 9.9367 | TiAl6Nb7 | ASTM F1295 | | | | | | | | | | | | | | | | | | | | | | | | | |
| S ₃ | CrCo-Legierungen | 2.4964 | CoCr20W15Ni | Haynes 25 | 20-40 | 5xd1 | 2xd1 | 0.010 | 0.020 | 0.030 | 0.040 | 0.050 | 0.065 | 0.080 | 0.100 | 0.120 | | | | | | | | | | | | | |
| | | | CrCoMo28 | ASTM F1537 | | | | | | | | | | | | | | | | | | | | | | | | | |
| H ₁ H ₂ | Stähle gehärtet < 55 HRC | 1.2510 | 100MnCrMoW4 | AISI O1 | 30-60 | 5xd1 | 1xd1 | 0.020 | 0.030 | 0.040 | 0.050 | 0.060 | 0.080 | 0.110 | 0.140 | 0.160 | | | | | | | | | | | | | |
| | | 1.2379 | X153CrMoV12 | AISI D2 | | | | | | | | | | | | | | | | | | | | | | | | | |