




CrazyDrill Cool 15 x d - uncoated

RECOMMENDATION FOR USE
● Excellent | ● Good | ○ Acceptable | ☒ Not recommended



DRILLING WITH INTERNAL COOLING | CUTTING DATA OVERVIEW



Materials group	Material	Mat. no.	DIN	AISI/ASTM/UNS	v _c		Q ₁	Q _x	f [mm/rev] [IPR]																																																											
					[m/min] [SFM]				Ød1																																																											
					Mid	High			0.8 mm .032"	1.0 mm .039"	1.25 mm .049"	1.5 mm .059"	2.0 mm .079"	2.5 mm .098"	3.0 mm .118"	4.0 mm .158"	35.0 mm .197"	6.0 mm .236"																																																		
P	Unalloyed carbon steel Rm < 800 N/mm²	1.0301	C10	AISI 1010	40 131	60 197	6xd1	2xd1	f	f	f	f	f	f	f	f	f	f	f	f	f																																															
		1.0401	C15	AISI 1015																																																																
		1.1191	C45E/CK45	AISI 1045																																																																
		1.0044	S275JR	AISI 1020																																																																
		1.0715	11SMn30	AISI 1215																																																																
	Low alloyed steel Rm > 900 N/mm²	1.5752	15NiCr13	ASTM 3415 / AISI 3310	40 131	60 197	6xd1	2xd1														f	f	f	f	f	f	f	f	f	f	f	f	f																																		
		1.7131	16MnCr5	AISI 5115																																																																
		1.3505	100Cr6	AISI 52100																																																																
		1.7225	42CrMo4	AISI 4140																																																																
		1.2842	90MnCrV8	AISI O2																																																																
	High alloyed tool steel Rm < 1200 N/mm²	1.2379	X153CrMoV12	AISI D2	20 66	40 131	6xd1	2xd1																											f	f	f	f	f	f	f	f	f	f	f	f	f																					
		1.2436	X210CrW12	AISI D4/D6																																																																
1.3343		HS6-5-2C	AISI M2 / UNS T11302																																																																	
1.3355		HS18-0-1	AISI T1 / UNS T12001																																																																	
M		Stainless steel ferritic	1.4016	X6Cr17					AISI 430 / UNS S43000					f	f	f	f	f	f	f	f																											f	f	f	f	f																
	1.4105		X6CrMoS17	AISI 430F																																																																
	1.4034		X46Cr13	AISI 420C																																																																
	1.4112		X90CrMoV18	AISI 440B																																																																
	Stainless steel martensitic	1.4542	X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH	Recommended: CrazyDrill Cool - coated																																																															
		1.4545	X5CrNiCuNb 15-5	ASTM 15-5 PH																																																																
		1.4301	X5CrNi 18-10	AISI 304																																																																
		1.4435	X2CrNiMo 18-14-3	AISI 316L																																																																
Stainless steel austenitic	1.4441	X2CrNiMo 18-15-3	AISI 316LM	Recommended: CrazyDrill Cool - coated																																																																
	1.4539	X1NiCrMoCu 25-20-5	AISI 904L																																																																	
	K	Cast iron	0.6020			GG20	ASTM 30	Recommended: CrazyDrill Cool - coated																																																												
			0.6030			GG30	ASTM 40B																																																													
0.7040			GGG40		ASTM 60-40-18																																																															
0.7060			GGG60		ASTM 80-60-03																																																															
N	Aluminium alloy wrought	3.2315	AlMgSi1		ASTM 6351	100 328	300 984	5xd1	1xd1	f	f	f	f	f	f	f	f	f	f	f	f																																															
		3.4365	AlZnMgCu1.5		ASTM 7075																																																															
	Aluminium alloy cast	3.2163	GD-AlSi9Cu3	ASTM A380	100 328	200 656	5xd1	1xd1	f													f	f	f	f	f	f	f	f	f	f	f																																				
		3.2381	GD-AlSi10Mg	UNS A03590																																																																
	Copper	2.004	Cu-OF / CW008A	UNS C10100	100 328	200 656	1.5xd1	1xd1																									f	f	f	f	f	f	f	f	f	f	f	f																								
		2.0065	Cu-ETP / CW004A	UNS C11000																																																																
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	100 328	140 459	1xd1	0.5xd1																																					f	f	f	f	f	f	f	f	f	f	f	f												
		2.036	CuZn40 CW509L	UNS C28000																																																																
	Brass, Bronze Rm < 400 N/mm²	2.0401	CuZn39Pb3 / CW614N	UNS C38500	80 262	120 394	2xd1	1xd1																																																	f	f	f	f	f	f	f	f	f	f	f	f
		2.102	CuSn6	UNS C51900																																																																
Bronze Rm < 600 N/mm²	2.0966	CuAl10Ni5Fe4	UNS C63000	80 262	120 394	10xd1	5xd1	f		f	f	f	f	f	f	f	f	f	f	f																																																
	2.096	CuAl9Mn2	UNS C63200																																																																	
S ₁	Super alloys	2.4856		Inconel 625																	f	f	f	f	f	f	f	f	f	f	f																																					
		2.4668		Inconel 718																																																																
		2.4617	NiMo28	Hastelloy B-2																																																																
		2.4665	NiCr22Fe18Mo	Hastelloy X																																																																
S ₂	Titanium pure	3.7035	Gr.2	ASTM B348 / F67	20 66	40 131	0.5xd1		0.25xd1																							f	f	f	f	f	f	f	f	f	f	f																										
		3.7065	Gr.4	ASTM B348 / F68																																																																
S ₂	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136	20 66	40 131	0.5xd1		0.25xd1																																		f	f	f	f	f	f	f	f	f	f	f															
		9.9367	TiAl6Nb7	ASTM F1295																																																																
S ₃	CrCo alloys	2.4964	CoCr20W15Ni	Haynes 25					f	f	f	f	f	f	f	f	f	f																																																		
			CrCoMo28	ASTM F1537																																																																
H ₁	Hardened steel < 55 HRC	1.2510	100MnCrMoW4	AISI O1															f	f	f	f	f	f	f	f	f	f																																								
		1.2379	X153CrMoV12	AISI D2																																																																
H ₂	Hardened steel ≥ 55 HRC	1.2379	X153CrMoV12	AISI D2																									f	f	f																							f	f	f	f	f	f	f								